



Technical Data

Rojo Alicante

TYPE: Marble

ORIGIN: Monovar, Spain

PHYSICO-MECHANICAL PROPERTIES

Compression strenght	94,61 MPa
Bending strenght	8,73 MPa
Volumetric weight	2,71 gm/cm ³
Friction wear resistance	2,42 mm
Porosity	0.30 %
Knoop micro-hardness	1951,96 MPa
Absorption coefficient	0.10 %
Impact test (minimum height)	30 cm

RECOMMENDED APPLICATIONS

Flooring, interior decoration, cladding.

Note: This technical data is only representative. Please do not consider it as 100% accurate or extremely updated.

Source: Incom Pastor